ASIA PACIFIC INDUSTRY GROUP CO., LIMITED
Tel +0086-551-64687285
Email sales@boppfilmsales.com
www.boppfilmsales.com · www.apigcl.com

BOPS technical data
产品技术资料 — 技术数据

Document No. 文件编号	Revision 版本	Issue date 签发日期	Document type 文件类型
APIG-BOPS-DATA-2026	**Rev. 2.0**	**2026-11-09**	**Technical Data / 技术数据**

1 • DOCUMENT INFORMATION 文档信息

Item 项目	Description 说明
Document type 文件类型	Technical Data / 技术数据
Subject 主题	BOPS technical data
Specification basis 规格依据	APIG product specification 亚太工业集团产品规格
Issue 签发	2026-11-09 · Rev. 2.0
Language 语言	Bilingual headings — English / 中文

2 • TECHNICAL CONTENT 技术内容

Product / packing view 1 产品 / 包装实拍 1

Technology data of BOPS polystyrene film shrinkage · Usage of BOPS polystyrene film shrinkage bottle labeling. Besides stick evenly to the bottle and shrink without rebound, it possess anti-crack and nice handle. ·
以下数据为本产品技术规格，随货签发检验记录。

3 • NOTES 说明

This document states the standard specification of the product. Values apply to the grades listed here; the tolerance range agreed in the order confirmation and the technical agreement prevails for any specific order. Batch test records are issued with the goods on request.

PHOTOS 实拍图片

PROPERTIES 性能	UNIT 单位		RESULT 指标	TEST STANDARD 测定方法
AVERAGE GAUGE 平均厚度	MICRON μm		50.4	-
THICKNESS TOLERRANCE(MAX) 厚度偏差	%		±5	
HAZE 雾度	%		3.6	ASTM D-1003
GLOSS 45° 光泽度	%		105.6	ASTM D-2457
TENSILE STRENGTH 抗拉强度	MPa	MD	35.7	JIS K7127
	MPa	TD	72	JIS K7127
ELONGATION AT BREAK 断裂伸长率	%	MD	345.6	JIS K7127
	%	TD	122.5	JIS K7127
MODULUS OF ELASTICITY 弹性模量	MPa	MD	1382	JIS K7127
		TD	1401	JIS K7127
HEAT SHRINKAGE 热收缩率	%	99℃ 10秒 MD	3.1	JIS Z1709
	%	TD	65.7	JIS Z1709
COF 摩擦系数	AA	AB	BB	ASTM D-1894
	0.293	0.313	0.287	





Product view 1 产品实拍 1

地址 ADD.: No.3399, Luzhou Ave., Baohe Dist., Hefei, Anhui 230051, China | 安徽省合肥市包河区庐州大道3399号
传真 Fax: +0086-551-64683490 **营业执照注册号 Business License Reg. No.:** 91340100575703313N
海关注册编码 Customs Reg. Code: 3401961393