ASIA PACIFIC INDUSTRY GROUP CO., LIMITED
Tel +0086-551-64687285
Email sales@boppfilmsales.com
www.boppfilmsales.com · www.apigcl.com

Asia Pacific -Water Based Pressure Adhesive For
胶粘剂 — 技术数据表

Document No. 文件编号	Revision 版本	Issue date 签发日期	Document type 文件类型
APIG-RD-20180921134729-2026	**Rev. 2.0**	**2026-11-09**	**Technical Data Sheet / 技术数据表**

1 • DOCUMENT INFORMATION 文档信息

Item 项目	Description 说明
Document type 文件类型	Technical Data Sheet / 技术数据表
Subject 主题	Asia Pacific -Water Based Pressure Adhesive For Films (TDS)
Specification basis 规格依据	APIG product specification 亚太工业集团产品规格
Issue 签发	2026-11-09 · Rev. 2.0
Language 语言	Bilingual headings — English / 中文

2 • TECHNICAL CONTENT 技术内容

number.: 91340100575703313N 离子性 阴离子 改性苯乙烯-丙烯酸酯乳液共聚物
水性自交联苯乙烯-丙烯酸酯共聚乳液，具有粘结力强、流动性好、涂布性 能优异等特点，适用于PP 透明、PP 白色、PP 银色、PP 合成纸、PP 珠 光等; PE 透明、PE 白色、PE 亮银等; PET 透明、PET 银色、PET 亮 白、PET 哑白, PVC 透明、PVC 白色、PVC 银色等离型塑料膜标签及广告材料的粘合。 □无毒、环保 □优异的耐候性 □涂布性能优异，适合转移涂布 □极长时间的持粘力，极佳平衡的初粘力和终粘力 外观 乳白色液体 pH 7.0-8.0 固含量 54±1% 粘度(25℃) 200-300cP □适用于PP、PE、PET、PVC 等膜标签及广告材料的粘合 □200 公斤/塑料桶
□产品应贮存在密闭容器内，避免冷冻及高温，建议正常贮存温度 在5℃~35℃，贮存期自包装之日起为6 个月
□可按非危险品运输 number.: 91340100575703313N Acrylic ester aqueous dispersion SA-233 is an adhesive specially designed for reverse gravure coaters, for the production of general purpose filmic labels (PP, PE, PVC, and PET etc.) or other pressure sensitive articles. □Non-yellowing □Repositionability □Excellent balance of tack and shear □Ideal for usein general clear and/or coloured polyolefinic film labels Milky white liquid pH 6.5-8.5 Solid content 50±1% Type of emulsion Anionic Viscosity (25℃) 100-200mPa·s Density (20℃) 1.02 g/cm3 Surface of the film Tacky, clear □General purpose polyolefinic film labels □Other pressure sensitive articles etc. □Available in 200 kg/ barrel or 1000 kg/ barrel (IBC) □Store products in tightly closed original containers at5-35℃ □Shelf life: 6-9 months from delivery date □According to non-dangerous goods transport

以下数据为本产品技术规格，随货签发检验记录。

3 • NOTES 说明

This document states the standard specification of the product. Values apply to the grades listed here; the tolerance range agreed in the order confirmation and the technical agreement prevails for any specific order. Batch test records are issued with the goods on request.

地址 ADD.: No.3399, Luzhou Ave., Baohe Dist., Hefei, Anhui 230051, China | 安徽省合肥市包河区庐州大道3399号
传真 Fax: +0086-551-64683490 **营业执照注册号 Business License Reg. No.:** 91340100575703313N
海关注册编码 Customs Reg. Code: 3401961393