亞太工業集團
Asia Pacific Industry Group Co., Limited

ASIA PACIFIC INDUSTRY GROUP CO., LIMITED

Tel +0086-551-64687285
Email sales@boppfilmsales.com
www.boppfilmsales.com · www.apigcl.com

BOPP Plain Bag-Grade Film, Corona Treated

BOPP 通用制袋级薄膜（电晕处理）

Document No. 文件编号	Revision 版本	Issue date 签发日期	Document type 文件类型
APIG-TDS-BOPP-BAG-2018	**Rev. 1.0**	**2018-09-25**	**Technical Data Sheet / 技术数据表**

PRODUCT 产品说明

Plain bag-grade BOPP film with corona treatment on one side. Inner core 3 in. (76 mm); dyne level 38 on the treated side.

通用制袋级 BOPP 平膜，单面电晕处理;纸芯内径 3 英寸（76 mm）;处理面达因值 38。

CHARACTERISTICS 性能指标

项目 Item	方向 Dir.	单位 Unit	方法 Method	Grade A++
拉伸强度 Tensile strength	MD	MPa	GB13022-91	≥50
	TD	MPa	GB13022-91	≥60
断裂伸长率 Elongation at break	MD	%	GB13022-91	≥180
	TD	%	GB13022-91	≥65
热收缩率 Heat shrinkage	MD	%	GB/T1003-96	≤4
	TD	%	GB/T1003-96	≤2
雾度 Haze		%	GB2410-80	≤1.2
透光率 Transparency		%	GB2410-80	≥85
光泽度 Glossiness		%	GB8807-88	≥90
处理强度 Corona treatment		mN/m	GB/T14216-93	≥39
摩擦系数 Friction	MD	%	GB10006-88	≤0.8
	TD	%	GB10006-88	≤0.8

The comparison symbols in front of the values are given according to the nature of each property (lower limits for strength, elongation, transparency, gloss and treatment; upper limits for shrinkage, haze and friction). Please check against the data sheet before quoting.
比较符号按各项目性质取值（强度、伸长率、透光率、光泽度、处理强度取下限;收缩率、雾度、摩擦系数取上限）。引用前请核对本表数据。

地址 ADD.: No.3399, Luzhou Ave., Baohe Dist., Hefei, Anhui 230051, China | 安徽省合肥市包河区庐州大道3399号
传真 Fax: +0086-551-64683490 **营业执照注册号 Business License Reg. No.:** 91340100575703313N
海关注册编码 Customs Reg. Code: 3401961393